

Product Description

A standard duty, conventional dense refractory castable.

Typical Product Data

Service Limit (°C)	1450	Aggregate	Chamotte
Recommended (Min %)	10.6	Installation by	Casting
Water Addition (Max %)	12.4		
Max Grain Size (mm)	8		

Typical Properties After Heating

	110°C	1000°C	1400°C
CCS (Mpa)	25.0	10.0	40.0
BD min (kg/m³)	1965	1875	1855
max (kg/m³)	2115	2025	2005
PLC (%)	±0.2	±0.4	±1.0
MOR (Mpa)	7		

Typical Chemical Properties

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	CaO	TiO ₂	Alkali
44.9	44.1	0.8	6.5	2.3	2.6

<i>Thermal Conductivity</i>	1.12	<i>W/mK @ 1000 °C</i>
<i>Shelf Life</i>	12	<i>Months</i>
<i>Standard Packaging</i>	25	<i>Kg Paper Bags</i>

Important Product Notes

Formerly Known as Hanlon 1450 CF

Water % used for QC Testing **11.5**

The published statistical data does not constitute a specification. Data is generated from production QC testing and is subject to variation.

Reference Document Number - PD	33	Latest Revision	17-Feb-09
--------------------------------	----	-----------------	-----------

Information of a technical nature is proprietary information and must be regarded as confidential.