

Product Description

A standard duty, abrasion resistant dense refractory castable.

Typical Product Data

Service Limit (°C)	1450	Aggregate	Chamotte
Recommended (Min %) Water Addition (Max %)	ARFG	Installation by	Gunning
Max Grain Size (mm)	3		

Typical Properties After Heating

	110°C	1000°C	1400°C
CCS (Mpa)	35.0	25.0	50.0
BD min (kg/m ³)	2025	1860	1795
max (kg/m ³)	2175	2010	1945
PLC (%)	±0.2	±0.4	-0.5 / +2.0
MOR (Mpa)	7		

Typical Chemical Properties

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	CaO	TiO ₂	Alkali
44.4	44.4	0.8	6.5	2.2	2.6

Thermal Conductivity 1.12 W/mK @ 1000 °C
Shelf Life 12 Months
Standard Packaging 25 Kg Paper Bags

Important Product Notes

Formerly Known as Hanlon 1450 ARGCF

All values are obtained from cast samples

Water % used for QC Testing **12.5**

The published statistical data does not constitute a specification. Data is generated from production QC testing and is subject to variation.

Reference Document Number - PD	146	Latest Revision	26-Feb-09
--------------------------------	-----	-----------------	-----------

Information of a technical nature is proprietary information and must be regarded as confidential.