

Product Description

A low cement refractory castable, which has been developed for easy installation.

Typical Product Data

Service Limit (°C)	1650	Aggregate	Chamotte
Recommended (Min %)	7.4	Installation by	Casting
Water Addition (Max %)	8.6		
Max Grain Size (mm)	5		

Typical Properties After Heating

	110 °C	1000 °C	1400 °C
CCS (Mpa)	74.0	74.0	101.8
BD min (kg/m ³)	2425	2425	2425
max (kg/m ³)	2575	2575	2575
PLC (%)	±0.2	±0.4	-1.3 / +0.5
MOR (Mpa)	8		

Typical Chemical Properties

Al ₂ O ₃	SiO ₂	Fe ₂ O ₃	CaO	TiO ₂	Alkali
61.4	31.7	0.8	2.8	1.5	1.8

Thermal Conductivity 1.92 W/mK @ 1000°C
Shelf Life 6 Months
Standard Packaging 25 Kg Paper Bags

Important Product Notes

Water % used for QC Testing **8**

The published statistical data does not constitute a specification. Data is generated from production QC testing and is subject to variation.

Reference Document Number - PD	186	Latest Revision	15-Mar-07
--------------------------------	-----	-----------------	-----------

Information of a technical nature is proprietary information and must be regarded as confidential.